

## Esband FX 17 both sides coated Specifications

	Side 1	Side 2
<b>Carcass</b>	Aramide special carcass	
<b>Coating</b>	FDA polyurethane, white smooth	FDA polyurethane, white T-profile
<b>Hardness</b>	80 ± 5 Shore A	80 ± 5 Shore A
<b>Abrasion resistance</b>	High	High
<b>Food contact approval</b>	Yes, FDA	Yes, FDA
<b>Coefficient of Friction</b>	Steel: 0.5 ± 0.1 μ Paper: 0.4 ± 0.1 μ	Steel: 0.3 ± 0.1 μ Paper: 0.6 ± 0.1 μ
<b>Temperature range</b>	-10° up to + 80° C	
<b>Anti-static</b>	Possible	
<b>Break strength per cm of width - shaft load*</b>	2300 N	
<b>Elongation per cm of width - shaft load*</b>	300 N: 0.3 up to 0.4% 600 N: 0.6 up to 0.7% 1000 N: 0.9 up to 1.0%	
<b>Elasticity - shaft load force per cm of width at 1% elongation*</b>	1040 ± 50 N	
<b>Minimum pulley diameter*</b>	20mm	
<b>Available standard sizes</b>	Length: 480 up to 4000mm Width: 5.0 up to 900mm Thickness: 1.3mm	
<b>Tolerances</b>	Length: ± 0.5% (min. +/- 2.5mm) Width: ± 0.5mm Thickness: ± 0.15mm	

\* at minimum belt thickness