

## Esband NE 17 Specifications

	Side 1	Side 2
<b>Carcass</b>	Aramide Special Carcass	
<b>Coating</b>	Neoprene Rubber profiled	Neoprene Rubber profiled
<b>Hardness</b>	75 ± 5 Shore A	75 ± 5 Shore A
<b>Abrasion resistance</b>	Medium	Medium
<b>Food contact approval</b>	No	No
<b>Coefficient of Friction</b>	Steel: 0.6 ± 0.1 μ Paper: 0.8 ± 0.1 μ	Steel: 0.6 ± 0.1 μ Paper: 0.8 ± 0.1 μ
<b>Temperature range</b>	-20 up to + 100 °C	
<b>Anti-static</b>	Yes	
<b>Break strength per cm of width - shaft load*</b>	2400 N	
<b>Elongation per cm of width - shaft load*</b>	300 N: 0.2 up to 0.4 % 600 N: 0.5 up to 0.7 % 1000 N: 0.9 up to 1.1 %	
<b>Elasticity - shaft load force per cm of width at 1% elongation*</b>	0.2 up to 0.4 %	
<b>Minimum pulley diameter*</b>	12mm	
<b>Available standard sizes</b>	Length: 180 up to 4600 mm Width: 3.0 up to 420 mm Thickness: 0.9 mm	
<b>Tolerances</b>	Length: ± 1.0 % (min. +/- 2.5 mm) Width: ± 0.5 mm Thickness: ± 0.15 mm	

\* at minimum belt thickness